

MATERIAL DATA SHEET

RHEINZINK- GRANUM EXTRA granite



- ELEGANT, LIGHT-COLOURED SURFACE, MATT LOOK WITH TYPICAL ZINC STRUCTURE
- EXCELLENT CORROSION RESISTANCE
- DURABLE AND WEATHER-RESISTANT
- EXTRAORDINARY COLOUR STABILITY

RHEINZINK GmbH & Co. KG
Bahnhofstraße 90
45711 Datteln · Germany
Tel.: +49 2363 605-490
E-Mail: info@rheinzink.com

www.rheinzink.com

BASIC-INFORMATION

The RHEINZINK-GRANUM EXTRA product line stands for an elegant, matt appearance. GRANUM EXTRA is characterised by its durable coating with exceptional colour stability and outstanding corrosion resistance. GRANUM EXTRA granite is the light-coloured surface variant that gives a hint of the typical zinc structure of the natural patina and is aesthetically pleasing and traditionally authentic in its simplicity. The material offers weather-resistant protection for a consistent appearance.

Specific weight 7.2 g/cm³

Building material class A1 (non-combustible)

Titanium zinc according to DIN EN 988

DELIVERY FORM

Standard widths	500 – 600 – 670 – 1000 mm
Standard thicknesses	0.70 – 0.80 mm – 1.00 mm
Protective film	Standard
Coil inner diameter	508 mm at ≥ 500 kg 300 mm at < 500 kg

IMPORTANT INSTALLATION INSTRUCTIONS

Bending radius	Minimum 1.75 mm, from 1.00 mm on 1.75 x t
Soldering recommendation	„Lösemittel EXTRA“ (company FELDER) Removal of the coating with cleaning fleece Soldering flux „ZD-Pro“ (company FELDER) overlap area 40 mm, Solder seam width 10 to 15 mm
Processing temperature	For sudden forming below 10 °C outside temperature, heating by hot air dryer
Protective film	Remove the film immediately after installation

Note:

Please request the RHEINZINK cleaning recommendations in the event of soiling caused by external influences or the environment. With these recommendations, RHEINZINK cannot guarantee that the appearance will be as good as new.

MATERIAL DATA SHEET

RHEINZINK-
GRANUM EXTRA granite

GRANITE

GRANUM EXTRA granite

ALLOY

Zinc	99.995% (Z1 according to DIN EN 1179)
Copper	0.10 – 0.18%
Titanium	0.06 – 0.12%
Aluminium	≤ 0.015%

CERTIFICATION

Quality management	Certified according to EN ISO 9001
Environmental management	Certified according to ISO 14001
Energy management	Certified according to 50001
Environmental product declaration	Certified according to ISO 14025, TYPE III and EN 15804 (basic material)

MECHANICAL-TECHNOLOGICAL PROPERTIES

0.2% yield strength (Rp0.2)	≥ 100 N/mm ²
Tensile strength (Rm)	≥ 150 N/mm ²
Breaking elongation (A50)	≥ 35%
Vickers hardness (HV3)	≥ 45
Folding tensile test	≥ 0.7
Ericksen cupping	≥ 8.0 mm

PHYSICAL AND CHEMICAL PROPERTIES

Melting point / range	420 °C
Boiling point / range	906 °C
Recrystallization limit	> 300 °C
Density	7.2 g/ cm ³
Expansion coefficient	
In the longitudinal direction	2,2 mm/m x 100 K
In the rolling transverse direction	1,7 mm/m x 100 K
Thermal conductivity	110 W/m · K
Specific thermal capacity	398 J/kg/K

COATING PROPERTIES

Corrosivity category according to DIN EN ISO 12 944-2	C5
RAL-colour*	RAL 0005000 Steel grey

* Colour tone values are approximate values in the as-delivered condition, deviations in the surface.